

Advance Mobility Improvement for Organic Field Effect Transistors (#5187)

A method to increase dramatically—by more than 2 orders of magnitude—the mobility of organic field effect transistors (OFETs)

Avishek Aiyar, David M. Collard, Rakesh Nambiar, and Elsa Reichmanis from the School of Chemical and Biomolecular Engineering at Georgia Tech have developed a method to increase dramatically—by more than 2 orders of magnitude—the mobility of organic field effect transistors (OFETs). Their operationally simple approach uses low-intensity ultrasound to aggregate solutions of poly(3-hexylthiophene) (P3HT) within chloroform (CHCl_3) or other common solvents. When these ultrasound-induced aggregates are deposited onto a substrate via spin-coating, the resulting polymer film exhibits significantly higher charge transport compared to other approaches. Specifically, irradiating a P3HT-containing CHCl_3 solution with 40 kHz (130 W) of ultrasound for less than 5 minutes increases the film's mobility to $2.6 \times 10^{-2} \text{ cm}^2/(\text{V}\cdot\text{s})$ compared with a mere $4.2 \times 10^{-4} \text{ cm}^2/(\text{V}\cdot\text{s})$. Achieving this 100-fold improvement in charge transport did not require any additional processing or special deposition techniques.

Benefits/Advantages

- **Dramatic increase in mobility:** Yields a 2-order-of-magnitude increase in charge transport
- **Fast:** Achieves 100-fold improvements after a mere 5 minutes of ultrasound
- **Simple:** Requires only low-intensity ultrasound and eliminates the need for dielectric surface modifications or post-deposition treatment of the device
- **Reproducible:** Provides more consistent results than other methods

Potential Commercial Applications

This technology provides an efficient approach for mass manufacturing high-performance large-area printed electronics for:

- Flexible integrated circuits
- Flexible electronic displays
- Medical implants and other biodegradable electronics
- Televisions (OLED) and large electronic displays
- Smart packaging
- Interactive media products (gadgets, cards, toys)
- Branding and security (counterfeiting mitigation and product compliance)
- Wearable communications devices
- Electronic paper, plastic/flexible electronics

- Solar cells
- Radio-frequency identification (RFID) tags
- Data/Memory storage
- Consumer electronics

Background/Context for This Invention

This technology was developed to provide a simpler, faster method to increase mobility/charge transport, improving the performance of electronic devices. Various methods exist for enhancing charge transport and field effect mobilities in organic thin-film transistors; however, these techniques have significant drawbacks. For example, thermal annealing followed by slow crystallization requires time-consuming processing at extremely low oxygen and moisture levels. Dielectric surface modification using self-assembled monolayers is difficult to achieve and also requires a moisture-free environment. Less complex methods exist, but they do not yield significant improvements in mobility without the use of high-purity, process-intensive synthesized polymers.

Avishek Aiyar

Senior Scientist

Dr. David M. Collard

Professor and Associate Dean, College of Sciences

Rakesh Nambiar

R&D Leader at DuPont

Dr. Elsa Reichmanis

Professor, Pete Silas Chair in Chemical Engineering, and Director of the Reichmanis Research Group – Georgia Tech School of Chemical & Biomolecular Engineering

More Information

Publications

For more information about this technology, please visit:

<https://licensing.research.gatech.edu/technology/advance-mobility-improvement-organic-field-effect-transistors>

Images:

The automated sequential delivery of multiple fluids. A varying number of delay gates imprinted in the branches are shown in the figure.

COVID-19 and flu saliva test on paper: (A) The automatic sequential delivery of multiple reagents required for virus test; (B) Water pouring into the device triggers the virus assay, allowing the presence of SARS-CoV-2 and influenza A & B viruses to be visually identified by the color changes in the corresponding detection spot

